



3202 34th Street, Valley, AL 36854

Telephone: 334-768-1262 or 1-800-554-7424 Fax: 334-768-1255

TextesT Report: 1199265 B1

Date: 4/25/2008

Page: 1 of 1

CLIENT: POLY-AMERICA, L.P.  
2000 W. Marshall Drive  
Grand Prairie, TX 75051

ATTN: Kyle Traylor

SAMPLE IDENTIFICATION: PE SHEETING  
SFFRO926062W  
PURCHASE ORDER #0287455

FLAMMABILITY				
NFPA 701 (2004) TEST 2		After Flame	Char Length	Drip Burn
<u>FOLDS, Modified</u>		<u>(Seconds)</u>	<u>(mm)</u>	<u>(Seconds)</u>
<u>MACHINE DIRECTION</u>				
SPECIMEN *	#1	0.0	310.0	0.0
	#2	0.0	305.0	0.0
	#3	0.0	330.0	0.0
	#4	0.0	310.0	0.0

\* Specimens were conditioned at least 24 hours at 20±5°C before testing.

CRITERIA: PASS/FAIL

REQUIREMENTS: CHAR: 1050 mm Maximum Individual  
DRIP BURN: 2 Seconds Maximum Individual  
AFTER FLAME: 2 Seconds Maximum Individual

COMMENTS: The submitted sample passes the requirements of NFPA 701 (2004) Test 2 Flammability, when tested in the machine direction.